

## Digimura 2.1 Smooth - Technical Specification

### Typical Data

Total Weight (gsm)	350
PVC Weight (gsm)	290
Substrate Weight (gsm)	60
Substrate Type	Non Woven Polyester
PVC Formulation	F69
Thickness (mm)	0.34
Emboss	Sandgrain
Printing Ink	Pigmented Solvent
Lacquer	Acrylic
Tensile Strength Kgf/cm	MD 4.6 TD 3.1
Tear Strength mN (average)	MD 2660 TD 2300
Lightfastness BSEN20105	Minimum Grade 6
Fire Resistance	BS476 Class "O"
Impact Resistance EN259	Pass
Cleaning & Maintenance	Digitally printed wallcoverings are washable. Moderate soiling can be removed with a warm detergent & a damp cloth using a dabbing action to lift the contamination. Rinse off with clean water & dry with a clean absorbent cloth, ensuring the surface is dry at skirting level. Always wash from the bottom upwards to avoid streaking. The use of bleach or abrasive powders is not recommended.